



LITHOPIX P 4

Chemical binder

Chemical basis

Sodium polyphosphate

Characteristics

Appearance	white granules
Bulk density	approx. 600 g/l
pH (1 %)	approx. 4
P ₂ O ₅ content	approx. 69 %
Na ₂ O content	approx. 29 %

Shelf-life / Packaging

24 months when stored properly and dry in closed containers | bags of 25 kg

Application

LITHOPIX P 4 is employed as a binder for SiO₂-based ramming and gunning mixes and for binding olivine.

The product is rapidly water-soluble and less hygroscopic.

LITHOPIX P 4 is mixed dry into the bodies. The amount to be added is 1 to 3 % of the solids content of the body, depending on the field of application.

The above results have been obtained from trials in our laboratory and plant.
In the light of changing conditions they can serve only as a guide and are therefore offered without obligation.
We ask you to observe the possible rights of third parties.

WhatsApp
Business

